



**INFINIA**  
DENTAL LAB

### Inter-Occlusal Space Requirements

Occlusal Space-----0.7mm~1.5mm

Cement Gap-----0.2mm

### Material Min Thickness

Zir Min Thickness-----0.5mm

Zir Facial Min Thickness-----0.8mm

(For better shape and Shade, we need this amount)

Emax Min Thickness-----0.5mm

Emax Facial Min Thickness-----0.8mm

Emax Monolithic Facial Min Thickness--0.2mm

Alloy Only Min Thickness-----0.2mm

PFM Min Thickness----- 1mm